

REPORT NUMBER: AU10124036-1
ORIGINAL ISSUE DATE: January 28, 2011

EVALUATION CENTER

Intertek Testing Services Ltd., Shanghai Jinqiao Branch
Building T52-8, No. 1201 Gui Qiao Road,
Jinqiao Development Area, Pudong District
Shanghai 201206

RENDERED TO

Jiangsu Xiecheng Science & Deve.Co., Ltd
Industrial Zone, Jinhua county Jiangsu, China

SAMPLE EVALUATED:

4 mm fire resistant aluminium composite panel

EVALUATION PROPERTY

Reaction to Fire

**Report of 4 mm fire resistant aluminium composite panel for compliance with
the applicable requirements of the following criteria:
EN 13501-1: 2007+A1:2009**

"This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program."

1 Table of Contents

1	Table of Contents.....	2
2	Introduction	3
3	Test Samples	3
3.1.	SAMPLE SELECTION	3
3.2.	SAMPLE AND ASSEMBLY DESCRIPTION.....	3
4	Testing and Evaluation Methods	4
4.1.	HEAT OF COMBUSTION TEST	4
4.2.	SINGLE BURNING ITEM TEST	4
4.3.	CLASSIFICATION CRITERIA	5
5	Testing and Evaluation Results	6
5.1.	RESULTS AND OBSERVATIONS	6
5.1.1.	Statement of Measurement Uncertainty	6
5.2.	CLASSIFICATION	6
6	Conclusion	7
7	Appendix A: Sample Photograph	8
8	Revision Page.....	9

2 Introduction

Intertek Testing Services has conducted testing for Jiangsu Xiecheng Science & Deve.Co., Ltd on fire resistant aluminium composite panel, to evaluate reaction to fire. The testing was conducted at the external approved facility. The classification was in accordance with the procedures given in EN 13501-1: 2002+A1: 2009. This evaluation began on December 27, 2010 and was completed on January 21, 2011.

3 Test Samples

3.1. SAMPLE SELECTION

Samples were submitted to Intertek directly from the client. Samples were not independently selected for testing. Samples were received at the Evaluation Center on December 24, 2010.

3.2. SAMPLE AND ASSEMBLY DESCRIPTION

The samples were identified as fire resistant aluminium composite panel and photographs were presented in Appendix A.

The description of the samples given below has been prepared from information provided by the sponsor of the test. All values quoted are nominal, unless tolerances are given.

General description		A composite comprising an inorganic core surrounded by coated aluminium facings
Product trade name		ALMINE
Overall thickness		4mm
Overall density / weight per unit area		8.12kg/m ² (4mm,alu 0.5mmX0.5mm)
Facing	Product reference	PVDF coating
	Generic type	Polyvinylidene Fluoride (PVDF) Coating
	Name of manufacturer	PPG
	Density / weight per unit area	0.93 g/cm ³
	Thickness	26*10 ⁻⁶ m
	Colour	Flash silver
	Application rate per coat	24.18g/m ²
Aluminium Substrate	Generic type	Aluminium
	Product reference	3003 H16 Alloy Aluminium
	Name of manufacturer	OPTION 1
	Thickness	0.5mm
	Colour	White

	Density	2.7g/cm ³
Adhesive	Product reference	High Molecular Adhesive Film
	Generic type	PE
	Name of manufacturer	OPTION 1
	Application rate	0.58%
	Application method	High temperature melt
Core	Generic type	inorganic
	Product reference	AL(OH)3
	Name of manufacturer	Jiangsu Xiecheng Science & Deve.Co., Ltd
	Thickness	3mm
	Colour	White
	Density	1.79g/cm ³
Adhesive	Product reference	High Molecular Adhesive Film
	Generic type	PE
	Name of manufacturer	OPTION 1
	Application rate	0.58%
	Application method	High temperature melt
Aluminium Substrate	Generic type	Aluminium
	Product reference	3003 H16 Alloy Aluminium
	Name of manufacturer	OPTION 1
	Thickness	0.5mm
	Colour	White
	Density	2.7g/cm ³

Note: OPTION 1 - The sponsor was unwilling to provide this information.

4 Testing and Evaluation Methods

4.1. HEAT OF COMBUSTION TEST

The test was conducted in accordance with EN ISO 1716. In this test, the test specimen of specified mass is burned under standardized conditions, at constant volume, in an atmosphere of oxygen, in a bomb calorimeter. The heat of combustion determined under the specified conditions is calculated on the basis of the observed temperature rise, taking account of heat loss and the latent heat of vaporization of water.

4.2. SINGLE BURNING ITEM TEST

The test was conducted in accordance with EN 13823. This test evaluates the potential contribution of a product to the development of a fire, under a fire situation simulating a single burning item near to the product.

4.3. CLASSIFICATION CRITERIA

The classification was determined in accordance with EN 13501-1: 2002+A1: 2009. The classes A2 with their corresponding fire performance are given in the table below.

Table- Classes of reaction to fire performance for construction products excluding floorings and linear pipe thermal insulation products

Class	Test Method(s)	Classification criteria	Additional classifications
A2	EN ISO 1716 and	$PCS \leq 3,0 \text{ MJ/Kg}^a$ and $PCS \leq 4,0 \text{ MJ/m}^2^b$ $PCS \leq 4,0 \text{ MJ/m}^2^c$ and $PCS \leq 3,0 \text{ MJ/Kg}^d$	-
	EN 13823	$FIGRA \leq 120 \text{ W/s}$ and $LFS < \text{edge of specimen}$ and $THR_{600s} \leq 7,5 \text{ MJ}$	Smoke production ^e and Flaming droplets/particles ^f

Note:

- For homogeneous products and substantial components of non-homogeneous products.
- For any external non-substantial component of non-homogeneous products.
- For any internal non-substantial component of non-homogeneous products.
- For the product as a whole.
- In the last phase of the development of the test procedure, modifications of the smoke measurement system have been introduced, the effect of which needs further investigation. This may result in a modification of the limit values and/or parameters for the evaluation of the smoke production.
 $s1 = \text{SMOGRA} \leq 30 \text{ m}^2/\text{s}^2$ and $\text{TSP}_{600s} \leq 50 \text{ m}^2$; $s2 = \text{SMOGRA} \leq 180 \text{ m}^2/\text{s}^2$ and $\text{TSP}_{600s} \leq 200 \text{ m}^2$; $s3 =$ not $s1$ or $s2$
- $d0 =$ no flaming droplets/ particles in EN 13823 within 600 s;
 $d1 =$ no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600s;
 $d2 =$ not $d0$ or $d1$.

Ignition of the paper in EN ISO 11925-2 results in a d2 classification.

5 Testing and Evaluation Results

5.1. RESULTS AND OBSERVATIONS

The test results were shown in Table below.

Method	Parameter		Result
EN ISO 1716	PCS	Facing, MJ/m ²	0.5
		Aluminium Substrate, MJ/kg	0.0
		Adhesive, MJ/m ²	2.1
		Core, MJ/kg	2.0
		Adhesive, MJ/m ²	2.1
		Aluminium Substrate, MJ/kg	0.0
		the whole product, MJ/kg	1.9
EN 13823	FIGRA, W/s		0.0
	THR _{600s} , MJ		0.0
	LFS		<Edge of Specimen
	SMOGRA		1
	TSP _{600s}		34
	Flaming Droplets/ Particles		No flaming droplets/ particles occur within 600s

5.1.1. Statement of Measurement Uncertainty

When determining the test result, measurement uncertainty has been considered.

5.2. CLASSIFICATION

The classification has been carried out in accordance with EN 13501-1.

Fire behaviour		Smoke production			Flaming Droplets	
A2	-	s	1	-	d	0

Reaction to fire classification: A2-s1-d0

6 Conclusion

The product identified and evaluated in this report has been tested in accordance with EN 13501-1: 2007+A1:2009. The results are presented in Section 5 of this test report and the classification of the sample is as below.

Reaction to fire classification: A2-s1-d0

The conclusions of this test report may not be used as part of the requirements for Intertek product certification. Authority to Mark must be issued for a product to become certified.

INTERTEK

Harrison

Reported by: _____

Harrison Li
Project Engineer, Building Products

Sun Sun

Reviewed by: _____

Sun Sun
Technical Leader, Building Products

7 Appendix A: Sample Photograph



Fig. 1 Before SBI Test



Fig. 2 Before SBI Test



Fig. 3 After SBI Test



Fig. 4 After SBI Test

8 Revision Page

Revision No.	Date	Changes	Author	Reviewer
0	January 28, 2011	First issue	Harrison Li	Sun Sun

END OF DOCUMENT
